

# Optical Detection of Ion-Channel Induced Proton Transport in Supported Phospholipid Bilayers

*Tsung-Han (Calvin) Yang<sup>†</sup>, Chanel K. Yee<sup>†1</sup>, Meri L. Amweg<sup>†</sup>, Seema Singh<sup>‡</sup>, Eric L. Kendall<sup>†</sup>, Andrew M. Dattelbaum<sup>§</sup>, Andrew P. Shreve<sup>§\*</sup>, C. Jeffrey Brinker<sup>‡¶\*</sup>, and Atul N. Parikh<sup>†\*</sup>*

<sup>†</sup>Departments of Applied Science, Biomedical Engineering and Chemical Engineering and Materials Science, University of California, Davis, CA 95616, <sup>‡</sup>Materials Science, Sandia National Laboratories, Albuquerque, NM 87106, <sup>§</sup>Materials Physics and Applications Division, Los Alamos National Laboratory, Los Alamos, NM 87545,

<sup>¶</sup>Department of Chemical Engineering, University of New Mexico, NM 87106

<sup>1</sup>Present address: Amgen Corporation, Thousand Oaks, CA.

## Contact

Atul N. Parikh  
University of California, Davis  
Davis, CA 95616  
Phone: 1 (530) 754-7055  
Fax: 1 (530) 752-2444  
[anparikh@ucdavis.edu](mailto:anparikh@ucdavis.edu)

**ABSTRACT** The integration of ion-channel transport functions with responses derived from nanostructured and nanoporous silica mesophase materials is demonstrated. Patterned thin-film mesophases consisting of alternating hydrophilic nanoporous regions and hydrophobic nanostructured regions allow for spatially localized proton transport via selective dimerization of gramicidin in lipid bilayers formed on the hydrophilic regions. The adjoining hydrophobic mesostructure doped with a pH sensitive dye reports the transport. The ease of integrating functional membranes and reporters through the use of patterned mesophases should enable high throughput studies of membrane transport.

The development of new responsive materials increasingly relies upon the integration of diverse functions into multi-component architectures that can be produced using self-assembly or other simple processing methods<sup>1</sup>. Along these lines, the coupling of functions derived from biological membranes<sup>2, 3</sup> to functions arising from nanostructured and nanocomposite materials<sup>4, 5</sup> is of importance. For example, significant recent advances in engineering ion-channels now enable modulation of ionic and molecular transport<sup>6, 7</sup>. However, the integration of methods to maintain functional ion channels on solid supports with methods to transduce channel-mediated transport into a detectable signal is required to enable on-chip and high-throughput studies of membrane transport phenomena<sup>8</sup>. Previous efforts have primarily focused on integrating channel transport with electrical transduction<sup>9, 10</sup>. Here, we present a design based on thin-film silica mesophase materials that is amenable to high-density arraying and that combines a region facilitating transmembrane proton transport with a surrounding reporter region containing a fast-response pH sensitive optical probe.

Our design, illustrated in Figure 1, incorporates several properties that enable proton transport and its optical transduction. The area in which transmembrane transport occurs consists of a supported lipid bilayer<sup>11</sup> formed on a mesoporous silica region of a patterned thin film. Gramicidin, a short helical polypeptide, is present in both leaflets of the fluid bilayer, permitting active ion-channel formation via lateral diffusion and interleaflet dimerization for subsequent proton transport<sup>12</sup>. Each such functional or transporter area is closely surrounded by regions that report on pH changes. These reporter, or transduction, areas consist of the fast-response, pH-sensitive dye fluorescein isothiocyanate (FITC) embedded in a mesostructured, surfactant-containing, silica

film<sup>13</sup>. In these regions, membrane transport functions are blocked by the presence of a stable, hydrophobic, self-assembled monolayer on the surface of the silica mesophase. The use of photochemically patterned thin films<sup>14</sup> to provide spatial separation of the reporter region and the transporter region yields the important advantage of allowing the use of mesoporous silica in the transporter region. In contrast to mesostructured regions, which are slightly hydrophobic (water contact angle  $\sim 40^\circ$ ) even prior to the addition of the blocking self-assembled monolayer, mesoporous silica provides a fully hydrated and hydrophilic surface (contact angle with water  $\sim 0^\circ$ ) for the formation of a stable, uniform and laterally fluid supported bilayer membrane<sup>15</sup>. Our patterning methods also allows for arraying the entire multi-functional unit in a high-density format, thus facilitating parallel, on-chip, and high-throughput studies of membrane transport phenomena<sup>8</sup>.

We prepare a continuous FITC-derivatized thin-film silica mesophase on a freshly oxidized silicon substrate by adopting a previously reported technique<sup>13, 16</sup>. Briefly, 10 mg FITC in 26 mL ethanol is mixed with 11  $\mu\text{L}$  of 3-aminopropyltriethoxysilane (APTES) and stirred for  $\sim 3$  h in dark. The resulting solution is then added to an acidic aqueous solution of surfactant doped tetraethylorthosilicate (TEOS). We used a common poly(ethylene) oxide-poly (propylene) oxide triblock copolymer (pluronic F127) as the organic structure-directing agent. The final composition of the mixture was 1 TEOS:  $6.3 \times 10^{-4}$  FITC:  $1.2 \times 10^{-3}$  APTES: 10.9 EtOH: 2.5 H<sub>2</sub>O: 0.012 HCl:  $3.9 \times 10^{-3}$  Pluronic F127. Thin-films of FITC-derivatized silica mesophases are then prepared by dip-coating a clean silicon wafer under ambient conditions at a pulling rate of 50 mm/min. After dip-coating, the samples are aged at room temperature in a desiccator for  $\sim 4$ -6 h, followed by a slow-curing at  $70^\circ\text{C}$  for  $\sim 2$  days. The films are then

coated with a monolayer of *n*-octadecyltrichlorosilane (OTS) following a classical solution self-assembly technique<sup>17</sup>. This treatment renders the FITC-derivatized mesophase surface uniformly hydrophobic (water contact angle > 100°). Following the OTS assembly, we produce spatial patterns of square-shaped, hydrophilic mesoporous elements by using a previously demonstrated photocalcination procedure in which the sample is illuminated through a photomask using short-wavelength (184-257 nm) UV light<sup>14</sup>. This process removes OTS, the F127 template, aminopropyl groups and FITC from the exposed areas and promotes further siloxane condensation in the exposed regions. As suggested in Figure 1, this treatment results in a thinner (determined by aqueous-phase imaging ellipsometry and step-profilometry to be about 35% thinner for typical 400 nm thick films used in our study) nanoporous film bounded by a thicker, F127 and FITC containing, nanostructured film corresponding to the unexposed regions. We confirm that the FITC-containing areas of the patterned film retain their pH reporting activity<sup>18</sup> by immersing the patterned substrates into aqueous solutions with pH values of 4, 7 and 10, and noting resulting substantial changes in FITC emission intensities (Figure 1e-g). The pH dependent FITC emission intensity within the mesostructured environment demonstrates a fast-response (several seconds) and a sigmoidal-like shape characterized by a rapid intensity rise between pH values of 6.5 and 8. Compared to the solution phase, this response curve is broader probably because of environmental effects<sup>13, 19</sup>

The patterned films are subsequently incubated with small unilamellar vesicles (SUVs) consisting of POPC lipid (1-palmitoyl-2-oleoyl-phosphatidylcholine), 0.1-0.2 mol % gramicidin, and 1 mol % fluorescent lipid, Texas Red-DHPE (Texas Red 1,2-

dihexadecanoyl-sn-glycero-3- phosphoethanolamine, triethylammonium salt ) to allow visualization of the membranes. Control experiments were performed using identical procedures but with POPC vesicles devoid of gramicidin.

As expected, the surface energy-dependent fusion of SUVs onto these patterned hydrophilic/hydrophobic films results in single lipid monolayers on the reporter (FITC- and F127 derivatized) hydrophobic regions, whereas full bilayers form on the transporter hydrophilic nanoporous islands of the patterned silica mesophase<sup>20</sup> (Fig 1). Further characterization of these co-existing lipid morphologies is provided below. Assuming all gramicidin is incorporated in the supported membranes (0.1 -0.2 mol % or  $1.67 \times 10^5$  molecules per leaflet within each  $100 \text{ um}^2$  bilayer region) and assuming  $0.6 \text{ nm}^2$  area per lipid molecule, the total surface density of gramicidin is estimated as  $5.6 \times 10^{-13} \text{ mol/cm}^2$  for both leaflets. Further, the equilibrium association constant of  $6.86 \times 10^{14}$  in  $\text{mol/cm}^2$  units<sup>21</sup> indicates that nearly all (~97%) gramicidin molecules within the bilayer regions are dimerized forming functional ion-channels.

Key results obtained are summarized in Figure 2. Fluorescence images obtained using a red emission filter, appropriate for Texas Red DHPE, establish the stability, integrity, and structural consistency of the bilayer in aqueous media at the three pH values examined. The adjustment of aqueous phase pH values was achieved simply by adding controlled amounts of HCl or NaOH to the aqueous phase. Images obtained using a green emission filter appropriate for FITC reveal substantial changes in emission intensity from the reporter region in the presence of gramicidin, with an increase of more than a factor of seven observed between pH values of 4 and 10. In

contrast, control experiments confirm that only small changes in FITC emission occur for POPC samples devoid of gramicidin (Supplemental Information, SI).

Additional experiments have been performed to validate the primary elements of the structure represented in Figure 1. These are discussed in turn below. *First*, spatially-resolved imaging ellipsometry and step profilometry data confirm that the photopatterned mesophase thin-films display a topographic corrugation: the FITC-doped silanized mesostructure in a representative sample measures at  $408 (\pm 4)$  nm thick film whereas the UV-exposed nanoporous region is  $260 (\pm 3)$  nm thick. These values agree well with 30-35% reduction in mesophase thicknesses upon (photo) calcination reported earlier<sup>15, 22</sup>. The transition region between the mesostructure and the mesoporous region yield intermediate values probably because of the thickness gradient within that region. *Second*, contact angle measurements confirm that photopatterned mesophases are amphiphilic. FITC-doped and OTS derivatized mesostructure retains high contact angles by water ( $\sim 104^\circ$ ) whereas UV-exposed nanoporous region is fully wettable by water (contact angle  $< 10^\circ$ ). *Third*, the fusion of SUVs on these amphiphilic surfaces (consisting of hydrophobic, FITC-coated reporter mesostructures and hydrophilic nanoporous transporter regions) results in the formation of a compliant co-existing monolayer and bilayer morphologies respectively, consistent with previous reports.<sup>20</sup> This is confirmed using a combination of imaging ellipsometry<sup>23</sup> and fluorescence microscopy<sup>20</sup> methods. An analysis of ellipsometry images reveal  $3.7 (\pm 0.3)$  nm film in the nanoporous region and  $1.9 (\pm 0.4)$  nm in the hydrophobic FITC region in good correspondence with thicknesses of homogeneous lipid monolayers (reporter region) and bilayers (transporter region)<sup>20</sup>. The fluorescence images of our samples reveal a bright

and homogeneous fluorescence in the mesoporous, transporter regions of the sample – consistent with a uniform bilayer formation<sup>24</sup>. The lateral fluidity in this region is verified using FRAP (SI). The significantly lower intensity in the reporter mesostructure surroundings (FITC- and F127 doped regions) appears counter-intuitive. This apparent discrepancy results from a well-known fluorescence interference effect which arises near a reflective surface<sup>25</sup>. In particular, reflection at the silicon surface produces a standing-wave modulation of the fluorescence intensity as distance perpendicular to the substrate surface is varied<sup>26</sup>. In our case, the topographic corrugation between the transporter and reporter regions places the Texas-red dye in these respective regions at about 148 nm apart in the z-direction, which in turn produces a very low intensity for the monolayer in the reporter region<sup>25</sup>. Circumventing this issue using much lower reflectivity glass as a substrate for the mesophase patterns produces the familiar fluorescence intensity contrast: the bilayer in the transporter region is about 1.7 times more intense than the monolayer<sup>20</sup>. *Fourth*, since gramicidin dimerization and its transport function depend upon lateral diffusion within the supported bilayer membrane<sup>9, 27</sup>, the presence of long-range fluidity in the membrane has been assessed using FRAP measurements. These results confirm  $1-2 \times 10^{-8}$  cm<sup>2</sup>/s diffusion constants for the Texas-red probe within both the monolayer and bilayer regions consistent with values reported previously.<sup>28</sup>

To establish that the lipid monolayer formed over the OTS covered reporter regions is laterally connected to the bilayer over the nanoporous transporter regions, we performed a modified fluorescence recovery after photobleaching (FRAP) experiment. Here, when all fluorescence emission from a bilayer region in the patterned architectures is



photobleached by repeated exposure to an intense excitation beam, subsequent recovery of the fluorescence is observed (Figure 3). Such a recovery necessarily requires the lateral diffusion of unbleached fluorophores from the surrounding monolayer region, indicating a substantial lateral connectivity between the lipid monolayer and the bilayer phases.

Further verification of the function of gramicidin and of the means to block transmembrane proton transport in the reporting regions is provided by a series of experiments on uniform (i.e., non-patterned) mesostructured thin films (SI). As described above, we prepared a uniform (unpatterned) film in which the silica mesophase material is rendered hydrophobic by self-assembling *n*-octadecyltrichlorosilane (OTS) onto the surface. Spreading of gramicidin-containing POPC vesicles on such a surface leads to a hybrid-bilayer membrane consisting of an OTS monolayer inner leaflet and a POPC monolayer outer leaflet. The gramicidin monomer is confined to the outer leaflet. Varying the solution pH values results in minimal change in the intensity of the FITC fluorescence intensity, indicating that pH equilibration of the mesophase film and the solution does not occur (SI). Thus, OTS is shown to be effective in blocking transmembrane proton transport.

Taken together, the results reported here confirm the essential features illustrated in the schematic structure in Figure 1. The formation of fluid lipid bilayers in the mesoporous regions of our samples allows trans-leaflet dimerization of gramicidin. These ion-channels then facilitate proton transport across the lipid bilayer. The transported protons are subsequently released in the confined aqueous phase at the

interface between the membrane and the mesoporous thin film, from where they are able to diffuse into the FITC-doped, surfactant-loaded nanopores of the transducing regions. In contrast, the gramicidin contained in the outer lipid monolayers supported on OTS cannot facilitate proton transport across the entire phospholipid plus OTS hybrid bilayer.

In summary, we have demonstrated a multi-functional, patterned, thin-film that enables the integration of transmembrane ion transport functions with optical transduction of transport processes. The ease of incorporating various optical (and other) reporters in sol-gel films should allow for detectability of a broad range of ions and molecules. Finally the simplicity of UV photolithography and other patterning methods afford the isolation of single functional units (such as shown in Figure 1) from adjacent ones in a dense pattern. Such simple engineering could enable parallel assays of membrane transport. Future studies in our laboratories are aimed towards these ends.

Support for this work was provided by The Office of Science, Department of Energy, and through a Nanomedicine Center grant from NIH (National Center for Biomimetic Nanoconductors).

## Figure Captions

Figure 1. **A materials construct for optical transduction of ion-channel induced proton transport.** (a) A schematic depiction of an ion-channel (gramicidin A) containing fluid phospholipid membrane on a FITC-derivatized patterned mesostructure/mesoporous silica thin film. The optical reporter region consists of a FITC-containing mesostructure coated with an *n*-octadecyltrichlorosilane monolayer, and the transporter region is a mesoporous silica substrate. A lipid bilayer in the transporter region enables gramicidin dimerization and subsequent proton transport. A hybrid bilayer in the reporter region effectively blocks the proton transport to the substrate. (b) A cross-sectional TEM image reveals the presence of nanoscale pores in a square-lattice in the transporter regions for photocalcined F127-templated nanoporous mesophase. (c-d) Typical epifluorescence images show the uniform emission from the reporter (green) and transporter (red) regions respectively. (e-g) FITC-derivatized and F127-doped mesophases exhibit solution pH dependent FITC emission (approximately at 1:4:7 for pH 4, 7, and 10) which is in general qualitative agreement with the expected pH dependence of fluorescein.

Figure 2. **Optical transduction of ion-channel induced proton transport.** Red and green-channel epifluorescence images for a Texas-red-DHPE doped POPC bilayer (top panels) and the same bilayer containing 0.1 mol % Gramicidin A (bottom panels) as a function of solution pH. FITC-containing mesostructure reporter regions appear green and Texas-red-DHPE containing mesoporous transporter regions appear red. The dramatic changes in the FITC emission for the gramicidin containing bilayer reveal an

optical response in the mesostructure reporter region induced by the proton transport in the transporter region.

**Figure 3. Fluidity, Uniformity, and Lateral Contiguity of the lipid membrane on patterned silica mesophases.** Time-lapse fluorescence micrographs from a red-channel movie recorded after photobleaching a gramicidin containing POPC bilayer (doped with 1 mol % Texas-red-DHPE) on the mesoporous region of the patterned mesostructure/mesoporous silica film. The square indicated as 1 was fully photobleached by exposures to an intense excitation beam in rapid succession. The recovery of the fluorescence in the bleached area confirms the lateral contiguity and fluidity of the lipid phases. Note also that full recovery of the initial fluorescence is not expected due to the confinement of some permanently bleached Texas-red DHPE molecules in the lower leaflet of the bilayer. The homogeneity of the fluorescence emission from the bilayer and the monolayer areas further confirm their lateral structural uniformities.

## References

1. Boncheva, M.; Gracias, D. H.; Jacobs, H. O.; Whitesides, G. M. *Proceedings of the National Academy of Sciences of the United States of America* **2002**, 99, (8), 4937-4940.
2. Edidin, M. *Nature Reviews Molecular Cell Biology* **2003**, 4, (5), 414-418.
3. Vereb, G.; Szollosi, J.; Matko, J.; Nagy, P.; Farkas, T.; Vigh, L.; Matyus, L.; Waldmann, T. A.; Damjanovich, S. *Proceedings of the National Academy of Sciences of the United States of America* **2003**, 100, (14), 8053-8058.
4. Brinker, C. J.; Lu, Y. F.; Sellinger, A.; Fan, H. Y. *Advanced Materials* **1999**, 11, (7), 579-+.
5. Soten, I.; Ozin, G. A. *Current Opinion in Colloid & Interface Science* **1999**, 4, (5), 325-337.
6. Bayley, H. *Current Opinion in Biotechnology* **1999**, 10, (1), 94-103.
7. Bayley, H.; Jayasinghe, L. *Molecular Membrane Biology* **2004**, 21, (4), 209-220.
8. Bayley, H.; Cremer, P. S. *Nature* **2001**, 413, (6852), 226-230.
9. Cornell, B. A.; BraachMaksvytis, V. L. B.; King, L. G.; Osman, P. D. J.; Raguse, B.; Wiczorek, L.; Pace, R. J. *Nature* **1997**, 387, (6633), 580-583.
10. Tien, H. T.; Salamon, Z.; Ottova, A. *Critical Reviews in Biomedical Engineering* **1991**, 18, (5), 323-340.
11. Sackmann, E. *Science* **1996**, 271, (5245), 43-48.
12. Woolley, G. A.; Wallace, B. A. *Journal of Membrane Biology* **1992**, 129, (2), 109-136.
13. Wirnsberger, G.; Scott, B. J.; Stucky, G. D. *Chemical Communications* **2001**, (01), 119-120.
14. Dattelbaum, A. M.; Amweg, M. L.; Ecke, L. E.; Yee, C. K.; Shreve, A. P.; Parikh, A. N. *Nano Letters* **2003**, 3, (6), 719-722.
15. Clark, T.; Ruiz, J. D.; Fan, H. Y.; Brinker, C. J.; Swanson, B. I.; Parikh, A. N. *Chemistry of Materials* **2000**, 12, (12), 3879-3884.
16. Fan, H. Y.; Lu, Y. F.; Stump, A.; Reed, S. T.; Baer, T.; Schunk, R.; Perez-Luna, V.; Lopez, G. P.; Brinker, C. J. *Nature* **2000**, 405, (6782), 56-60.
17. Sagiv, J. *Journal of the American Chemical Society* **1980**, 102, (1), 92-98.
18. Yguerabide, J.; Talavera, E.; Alvarez, J. M.; Quintero, B. *Photochemistry and Photobiology* **1994**, 60, (5), 435-441.
19. Yang, L.; Saavedra, S. S. *Analytical Chemistry* **1995**, 67, (8), 1307-1314.
20. Howland, M. C.; Sapuri-Butti, A. R.; Dixit, S. S.; Dattelbaum, A. M.; Shreve, A. P.; Parikh, A. N. *Journal of the American Chemical Society* **2005**, 127, (18), 6752-6765.
21. Davis, R. W.; Patrick, E. L.; Meyer, L. A.; Ortiz, T. P.; Marshall, J. A.; Keller, D. J.; Brozik, S. M.; Brozik, J. A. *Journal of Physical Chemistry B* **2004**, 108, (39), 15364-15369.
22. Lu, Y. F.; Ganguli, R.; Drewien, C. A.; Anderson, M. T.; Brinker, C. J.; Gong, W. L.; Guo, Y. X.; Soye, H.; Dunn, B.; Huang, M. H.; Zink, J. I. *Nature* **1997**, 389, (6649), 364-368.
23. Howland, M. C.; Szmodis, A. W.; Sani, B.; Parikh, A. N. *Biophysical Journal* **2007**, 92, (4), 1306-1317.
24. Doshi, D. A.; Dattelbaum, A. M.; Watkins, E. B.; Brinker, C. J.; Swanson, B. I.; Shreve, A. P.; Parikh, A. N.; Majewski, J. *Langmuir* **2005**, 21, (7), 2865-2870.

25. Lambacher, A.; Fromherz, P. *Journal of the Optical Society of America B-Optical Physics* **2002**, 19, (6), 1435-1453.
26. Wong, A. P.; Groves, J. T. *Proceedings of the National Academy of Sciences of the United States of America* **2002**, 99, (22), 14147-14152.
27. Hwang, T. C.; Koeppe, R. E.; Andersen, O. S. *Biochemistry* **2003**, 42, (46), 13646-13658.
28. Cremer, P. S.; Boxer, S. G. *Journal of Physical Chemistry B* **1999**, 103, (13), 2554-2559.

## Table of Contents Graphics



